



## Low Fuming Bronze (RBCuZn-C)

### Specifications:

AWS A5.8 / ASME SFA5.8 Class RBCuZn-C

### Description:

Low Fuming Bronze is available in bare and flux coated. It is a machinable brazing alloy used on steels, copper alloys, nickel alloys, and stainless steel. Low Fuming Bronze has a high tensile strength and good ductility. The weld deposits are non-porous for leak proof joints for water, oil and gas lines. The weld deposit freezes rapidly from fluid to a plastic state. Preheat is required for some applications and a brazing flux is recommended.

### Typical Chemical Composition:

Copper	56.0 – 60.0
Zinc Balance Tin	0.80 – 1.10
Iron	0.25 – 1.20
Lead*	0.05 max.
Manganese	0.01 – 0.50
Aluminum*	0.01 max.
Silicon	0.04 – 0.15
Others	0.50 max.

\*included in others

### Typical Mechanical Properties:

Tensile Strength	65,000 psi, Avg.
Elongation, in 2 in.	25%
Brinnell Hardness	96
Melting Point	1630°F
Solidification	1595°F

### Available Sizes:

1/16" (1.6mm), 3/32" (2.4mm), 1/8" (3.2mm), 5/32" (4.0MM), 3/16" (4.8MM), 1/4" (6.4MM), 5/16" (8.0MM), 3/8" (9.5MM), 1/2" (13.0MM)

Notice: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

**Edmonton, AB Office**  
8804 51 Ave  
Edmonton, AB T6E 5E8  
Phone: 780-468-1777  
Fax 780-468-1758

**Chilliwack, BC Corporate**  
Unit A, 44636 Yale Rd West  
Chilliwack, BC V2R 0G5  
Phone: 604-701-6533  
Fax 604-701-6559

**Surrey, BC Office**  
Unit 11, 13085 115 Ave  
Surrey, BC V3R 4S7  
Phone: 1-877-233-1378  
Fax: 604-701-6559

**Saskatoon, SK Office**  
Unit#8, 401 Pakwa Place  
Saskatoon, SK S7L 5Z9  
Phone: 306-974-9750  
Fax 306-974-9752

**Prince George**  
1557 South Lyon St  
Prince George, BC V2M 1T3  
Phone: 250-562-8922  
Fax: 250-562-8927